

## FERMACELL Gypsum Fibreboards

### Description of material

Homogeneous, gypsum-based dry construction board with a paper fibre matrix, sealed at the factory.

### Areas of application

For interior application on walls, ceilings and floors.

### Approvals

Building inspectorate approval	ETA-03/0050
Construction material to DIN EN 13501-1	Non-flammable, A2
Board thickness	10 / 12.5 / 15 / 18 mm

### Dimensional tolerances at constant humidity for standard board sizes

Length, width	+ 0 / - 2 mm
Diagonal difference	≤ 2 mm
Thickness tolerance	± 0.2 mm

### Characteristic values

Density	1150 ± 50 kg/m <sup>3</sup>
Water vapour diffusion resistance coefficient	μ = 13
Thermal conductivity	λ = 0.32 W/mK
Specific heat capacity	c = 1.1 kJ/kgK
Brinell hardness	30 N/mm <sup>2</sup>
Swelling of thickness of 24 h immersion in water	< 2%
Coefficient of thermal expansion	0.001 %/K
Expansion / Shrinkage in response to 30 % change in relative humidity (20 °C)	0.25 mm/m
Moisture content at 65 % relative humidity and 20 °C air temperature	1.3%
pH value	7 - 8

For further data and information please refer to the European Technical Approval ETA-03/0050.

### Surfaces

Sanded front and rear faces, with production data and approvals printed on rear face.

### Storage

Packed and laid flat on pallets; protect against moisture, especially rain.

### Application

Cut with conventional woodworking tools; generally, carbide-tipped tools should be used when cutting to size.

### Distance between support frame/studs

Wall	≤ Board thickness [mm] x 50
Ceiling	≤ Board thickness [mm] x 35

### Final Finish

Trowel-applied FST, painted, plastered or tiled surfaces.



### FERMACELL Customer Information:

Fon: +49 203 501 90 40  
 Fax: +49 203 501 90 80  
 E-mail: [Info@xella.com](mailto:Info@xella.com)  
[www.xella.com](http://www.xella.com)